



CEWELD NiCro 601 Tig

TYPE	Nickel-Chromium-Aluminum alloy for TIG welding Alloy 601.										
ANWENDUNGEN	CEWELD® 601 Tig is used for severe applications where the exposure temperature can exceed 2100°F [1150°C].										
EIGENSCHAFTEN	Excellent resistance against corrosion and oxidation and suitable for applications when exposed to hydrogen sulfide or sulfur dioxide.										
KLASSIFIKATION	AWS	A 5.14: ER NiCrFe-11									
	EN ISO	18274: S Ni 6601(NiCr23Fe15Al)									
	F-nr	43									
	FM	6									
GEEIGNET FÜR	The nominal composition (wt.-%) of filler metal of this classification is 61 Ni, 23 Cr, 14 Fe, and 1.4 Al. Filler metal of this classification is used for welding nickel-chromium-iron-aluminum alloy (ASTM B 166, B 167, and B 168 having UNS number N06601) to itself and to other high-temperature compositions.										
ZULASSUNGEN											
SCHWEISSPOSITIONEN	     										
TYPISCHE CHEMISCHE ANALYSE DES FÜLLMETALLS (%)	C	Si	Mn	P	S	Cr	Ni	Fe	Cu	Al	
	0.08	0.27	0.9	0.01	0.01	23	61	15	0.1	1.5	
MECHANISCHE GÜTEWERTE	Heat Treatment			R _{P0,2} (MPa)		R _m (MPa)		A ₅ (%)		Hardness	
	As Welded					660		48		HRc	
RÜCKTROCKNUNG	Not required										
GAS ACC. EN ISO 14175	I1										



CEWELD NiCro 601 Tig

NICRO 601 TIG 1,6 X
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663418302

NICRO 601 TIG 2,0 X 914MM

Packaging	KG/unit	EanCode
Tube	4,54	8720663418319

NICRO 601 TIG 2,4 X 914MM

Packaging	KG/unit	EanCode
Tube	4,54	8720663418326