



CEWELD NiCrBSi 4 Tig (Colmonoy 4)

TYPE	Nickel based Tig filler metal for hardfacing and overlay applications.					
ANWENDUNGEN	NiCrBSi 4 TIG offers outstanding metallurgical and physical properties making them ideally suited to solving wear mechanisms such as abrasion, erosion, corrosion and high-temperatures encountered in service.					
EIGENSCHAFTEN	This nickel based alloy offers superior wear protection, retaining its hardness up to 600°C (1000°F) with significant resistance to oxidation.					
KLASSIFIKATION	AWS	A 5.21: ERNiCr-A				
GEEIGNET FÜR	UNS N99644, DELORO 40 Alloy, Colmonoy 4 Aircraft gas turbines, steam turbine powerplants, turbochargers and valves in reciprocating engines, prosthetic devices, heat treating equipment, pollution control equipment, coal gasification and liquefaction systems, and components in pulp and paper mills.					
ZULASSUNGEN						
SCHWEISSPOSITIONEN	     					
TYPISCHE CHEMISCHE ANALYSE DES FÜLLMETALLS (%)	C	Ni	Cr	B	Si	Fe
	0.4	Rem.	10	2.4	2.1	2.8
MECHANISCHE GÜTEWERTE	Heat Treatment		R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness
	As Welded					40 HRC
RÜCKTROCKNUNG	Not required					
GAS ACC. EN ISO 14175	I1					