

CEWELD E 9016-B9

TYPE Basic, Cr and Mo-alloyed electrode for heat resistant steels T/P91 and T/P92

ANWENDUNGEN Headers, main steam piping and turbine casings, in fossil fuelled power generating plants. Oil refineries and coal liquefaction and gasification plants. Preheat and Interpas temperature 200°C - 300°C.

EIGENSCHAFTEN CEWELD® E 9016-B9 is designed to weld equivalent 'type T91' T92 CrMo steels modified with small additions of Tungsten and Vanadium to give improved long term creep properties. These consumables are specifically intended for high integrity structural service at elevated temperature so the minor alloy additions responsible for its creep strength are kept above the minimum considered necessary to ensure satisfactory performance. In this case, weldments will be weakest in the softened (intercritical) HAZ region of parent material, as indicated by so-called 'type IV' failure in transverse weld creep tests.

KLASSIFIKATION

AWS	A 5.5: E9016-B91
EN ISO	3580-A: E CrMo91
F-nr	4
FM	4

GEEIGNET FÜR **9%Cr, 1%Mo, VNb**
1.7389, 1.7386, 1.4922, 1.4935, 1.4904, 1.4903, 1.4955,
X11CrMo9-1, X12CrMo9.1, X20CrMoV10-1, X10CrMoVNb9-1, GX12CrMoVNbN9-1
ASTM Grade 91, T91, P91, F91, FP91, WP91, C12A
STPA28, STBA28

ZULASSUNGEN CE

SCHWEISSPOSITIONEN



**TYPISCHE CHEMISCHE
ANALYSE DES
SCHWEISSMETALLS (%)**


C	Si	Mn	P	S	Cr	Ni	Mo	Nb	V	N
0.1	0.3	0.9	0.008	0.008	9	0.5	1	0.08	0.2	0.03

MECHANISCHE GÜTEWERTE

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A5 (%)	Impact Energy (J) ISO-V	Hardness
				RT	
As Welded	550	680	18	60	HRc

RÜCKTROCKNUNG 400°C / 1 hr

GAS ACC. EN ISO 14175



CEWELD E 9016-B9

E 9016-B9 3,2 X 350MM

Packaging	KG/unit	EanCode
VAC pack	1,9	8720663401465