



CEWELD NiFe 55 Tig

TYPE	Nickel Iron welding rod for joining multiple pass welding cast iron. (NiFe-2, 2.4472)							
APPLICATIONS	CEWELD® NiFe 55 Tig is suitable for welding mild and low alloy steels which are exposed to temperatures up to 450C. Multiple pass welding of spheroidal graphite cast irons and neutral tempered (black) malleable cast irons. Cast Iron repairs, rebuilding shafts, wheels, critical joints between steel and cast iron etc							
PROPERTIES	CEWELD® NiFe 55 Tig is a nickel Iron based filler metal for joint welding and claddings on cast Iron. Very wel suited also for dissimilar welding between cast iron and high alloyed stainless and heat resistant steels or mild steels. Excellent Weldability with extreme crack resistance with a ductile weld deposit. Good welding and wetting characteristics and high resistance against porosity. The weld metal is corrosion and heat resistant. Very well suitable for welding with robotics or automated processes.							
CLASSIFICATION	AWS EN ISO W.Nr.	A 5.15: E NiFe-Cl 1071: S C NiFe-2 2.4472						
SUITABLE FOR	Grey cast iron, malleable, nodular : NF A 32-101 : FGL 150, 200, 250, 300, 350, 400. NF A 32-201 : FGS 370-17, 400-12, 500-7, 600-3, 700-2. NF A 32-702 : MN 350-10, 380-18, 450-6, 350-4, 650-3. DIN 1691 : CG-14, 18, 25, 30. DIN 1693 : GGG-40, 50, 60, 70. DIN 1692 : GTS-35, 45, 55, 65, 70.							
APPROVALS								
WELDING POSITIONS	PAPBPCPDPEPFPG							
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	P	S	Ni	Fe	Cu
	0.01	0.13	0.7	0.005	0.001	55	Rem.	0.03
MECHANICAL PROPERTIES	Heat Treatment		R _{p0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness		
	As Welded		300	450	8	HRc		
REDRYING	Not required							
GAS ACC. EN ISO 14175	I1							



CEWELD NiFe 55 Tig

NIFE 55 TIG 1,6 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663424181
NIFE 55 TIG 2,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663420756
	Tube	5	8720663417817
NIFE 55 TIG 2,4 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663420763