



CEWELD 4830 Kb

TYPE	Basic electrode for heat resistant stainless steel SMAW welding.		
APPLICATIONS	Joining and cladding of fully austenitic heat resistant CrNi-steels of the same kind and similar Cast steels.		
PROPERTIES	High corrosion resistance and excellent weldability on both AC and DC+. The weld deposit is scale resistant up to 1000 °C		
CLASSIFICATION	EN ISO	3581-A: E Z 25 24 Nb B 32	
	W.Nr.	1.4830	
	FM	5	
SUITABLE FOR	W.Nr: 1.4855, 1.4845		

APPROVALS

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)


C	Cr	Ni	Nb
0.24	24.4	24.2	1.15

MECHANICAL PROPERTIES

Heat Treatment	R _{p0.2} (MPa)	R _m (MPa)	A5 (%)	Hardness
As Welded	400	600	10	HRc

REDRYING 300°C / 2 hr

GAS ACC. EN ISO 14175



CEWELD 4830 Kb

4830 KB 3,2 X 350MM

Packaging	KG/unit	EanCode
Can	2,5	8720663415691