



CEWELD L-Ag55Sn

TYPE High Silver containing Cadmium free brazing Alloy.

APPLICATIONS Joining: Steels, Cast iron, Copper, Copper alloys, Stainless steel, Nickel and Nickel alloys. Also suitable for dissimilar joints between these metals. Do not use this alloy above working temperatures of 200 °C

PROPRIÉTÉS High silver containing universal silver brazing alloy without Cadmium with low operating temperature and high mechanical properties. Due to the addition of Sn. this alloy will show a bright looking joint and is more capillary then the standard silver brazing alloys.
Flux/Paste: CEWELD Super-Flux

CLASSIFICATION AWS A 5.8: BAg-7
EN ISO 17672: Ag 156

CONVIENT POUR Brazing: Steels, Cast iron, Copper, Copper alloys, Stainless steel, Nickel and Nickel alloys. Also suitable for dissimilar joints between these metals.

AGRÉMENTS

POSITIONS DE SOUDAGE



**ANALYSE CHIMIQUE
TYPIQUE DU MÉTAL
D'APPORT (%)**

Cu	Zn	Sn	Ag
22	18	5	56

PROPRIÉTÉS MÉCANIQUES

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness
As Welded		400		HRc

ETUVAGE Not required

MELTING RANGE 620 - 655°C

GAS ACC. EN ISO 14175



CEWELD L-Ag55Sn

L-AG55SN 1,0MM

Packaging	KG/unit	EanCode
D-300	10	8720663422279