



CEWELD E NiTi3

TYPE	Nickel based welding electrode for DC +.	
APPLICATIONS	CEWELD E NiTi3 is developed for welding and cladding Nickel 200 and Nickel 201. This alloy is also suited for surfacing of steel. Dissimilar welding applications of filler metal NiTi3 include joining Nickel 200 and 201 to stainless steels, copper-nickel alloys, and Monel alloys. It is also used for joining Monel alloys and copper-nickel alloys to carbon steels, and for joining copper-nickel alloys to Inconel or Incoloy Alloys.	
PROPRIÉTÉS	The reaction of titanium with carbon maintains a low level of free carbon and enables the filler metal to be used with Nickel 201. The weld metal has good corrosion resistance, particularly in alkali's.	
CLASSIFICATION	AWS EN ISO W.Nr. F-nr FM	A 5.11: E Ni-1 14172: E Ni 2061 2.4156 41 6
CONVIENT POUR	Ni 2061 (NiTi3) W.Nr: 2.4060, 2.4061, 2.4062, 2.4066, 2.4068, 2.4106, 2.4108, 2.4109, 2.4110, 2.4116, 2.4122, 2.4128, 2.4170, 2.4175 Ni 99.6 ; Ni 99.2 ; LC-Ni 99.6 ; LC-Ni 99, Ni 99.4Fe, NiMn 1, NiMn 1C, NiMn 1,5, NiMn 2, NiMn 3Al, NiMn 5, NiAl 4Ti, G-Ni 95, G-Ni 93C ASTM B160, B161, B162, B163 UNS: N02200, N02201, N02205 Alloy: 200, 201, 205, Monell	

AGRÉMENTS

POSITIONS DE SOUDAGE



ANALYSE CHIMIQUE TYPIQUE DU MÉTAL DE SOUDURE (%)

C	Si	Mn	Ni	Ti	Fe	Cu
0.08	1	0.6	Rem.	3	0.5	0.1

PROPRIÉTÉS MÉCANIQUES

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V	Hardness
				RT	
As Welded	330	510	28	160	HRc

ETUVAGE Not required

GAS ACC. EN ISO 14175



CEWELD E NiTi3

E NIT13 2,5 X 350MM

Packaging	KG/unit	EanCode
Can	2,27	8720663419156

E NIT13 3,2 X 350MM

Packaging	KG/unit	EanCode
Can	2,27	8720663419163

E NIT13 4,0 X 350MM

Packaging	KG/unit	EanCode
Can	2,27	8720663417671