



CEWELD S3Si

TYPE	Solid drawn copper coated wire for the SAW process		
APPLICATIONS	Pipe work; offshore, pressure vessels, bridge, crane building, apparatus, and steam turbine construction.		
PROPRIÉTÉS	Excellent mechanical strength and welding properties due to a increased manganese and silicon content. S3Si is best to be used with FL 155 high basic agglomerated flux to obtain neutral action on metallurgical chemistry and excellent subzero impact properties down to -60°C.		
CLASSIFICATION	AWS	A 5.17: EH12K, A 5.23: EH12K	
	EN ISO	14171-A: S3Si	
	W.Nr.	1.0496	
	F-nr	6	
	FM	1	

CONVIENT POUR	Materials	DIN	EN	ASTM
	shipbuilding	A, B, D, E, AH 32 - EH 36	same	Typical
	Unalloyed steels	St 33, St 37-2 - St 52-3	S185 - S355	A 258 / A 516
	boiler steels	H I, H III, 17Mn4, 19Mn5	P235GH, P355GH	A 662 / A 387
	pipe steels	St 35.8, St 45.8	P235T1/T2, P460NL2	A 738 / A 612
	-	StE 210.7 TM, StE 445.7 TM	L210 - L445MB	A 299
	Fine grain steels	StE 255 to StE 460	S235 - S460QL1	-
	API-standard	X 42, X65, X 70	X 42, X65, X 70	-

AGRÉMENTS DNV, Lloyds

POSITIONS DE SOUDAGE			
----------------------	---	---	---

ANALYSE CHIMIQUE TYPIQUE DU MÉTAL D'APPORT (%)	C	Si	Mn	P	S
	0.1	0.35	1.75	0.015	0.015

PROPRIÉTÉS MÉCANIQUES	Heat Treatment	R _{p0.2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V			Hardness
					RT	-40°C	-60°C	
	As Welded	485	580	27	120	100	60	HRc

ETUVAGE Not required

GAS ACC. EN ISO 14175



CEWELD S3Si

S3Si 2,4MM

Packaging	KG/unit	EanCode
Drum	300	8720663404510
K-415	25	8720663404503

S3Si 3,2MM

Packaging	KG/unit	EanCode
K-415	27	8720663404527

S3Si 4,0MM

Packaging	KG/unit	EanCode
K-415	25	8720663404534