



CEWELD AA 316L Tig

TYPE	Flux cored stainless steel welding wire for Tig welding							
TOEPASSINGEN	Boilers, shipbuilding, machinery, offshore application, foundries, chemical industry, root pass welding when backing gas is not available or preferred.							
EIGENSCHAPPEN	Flux cored wire with slag support for high productivity welding especially for root welding. The slag is self detaching and offers a unique protection against oxidation on the reverse side of the root pass. Saving the cost for back shielding gas and purging time makes AA 316L Tig a very economical option.							
CLASSIFICATIE	AWS	A 5.22: R316LT1-5						
	W.Nr.	1.4430						
	F-nr	6						
	FM	5						
GESCHIKT VOOR	ISO 15608: 8.1 Austenit ≤ 19 % Cr , TÜV 1000: Gr. 21-30, 1.4583, 1.4435, 1.4436, 1.4404, 1.4406, 1.4408, 1.4401, 1.4571, 1.4580, 1.4406 X102CrNiMoNb 18 12, X2CrNiMo 18 14 3 (TP), X4CrNiMo 17 13 3, X2CrNiMo 17 12 2 (TP), X 5CrNiMo 19 11 2, X4CrNiMo 17 12 2 (TP), X6CrNiMo 17 12 2, X6CrNiMoNb 17 12 3, X2CrNiMoN 17 12 3 (TP) 316Cb, 316L, 316L, 316LN, 316H, 316, 316Ti, 316Cb, 316LN UNS S31640, UNS S31603, UNS S31653, UNS S31600, UNS S31635							
GOEDKEURINGEN								
LASPOSITIES	PAPBPCPDPEPF							
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	P	S	Cr	Ni	Mo
	0.02	0.9	1.6	0.015	0.015	19	13	2.3
MECHANISCHE WAARDEN	Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness	
	As Welded	440	600	38	RT		HRc	
HERDROGEN	Not required							
GAS ACC. EN ISO 14175	I1							



CEWELD AA 316L Tig

AA 316L TIG 2,2 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663413628