




CEWELD AA M CrMo2

TYPE	Seamless metal core wire for heat and creep resistant applications.							
TOEPASSINGEN	Construction of containers, boilers, machines and pipe work. Steam boilers and turbines construction.							
EIGENSCHAPPEN	Good arc restriking even with cold wire tip, suitable for robot applications. Ideal for use of short arc and spray arc. Excellent gap bridging for root welding. High-efficiency type for economic production of creep resistant steels and pressure-hydrogen-resistant 2¼Cr1Mo-steels. Due to the seamless production process the hydrogen content is below 3ml/100g weld metal even after long storage in unconditioned condition.							
CLASSIFICATIE	AWS	A 5.28: E90C-B3 H4						
	EN ISO	17634-A: T CrMo2 M M21 3 H5						
	F-nr	6						
	FM	3						
GESCHIKT VOOR	2,25% Cr, 1% Mo ISO 15608: ~5,2 (1,5 % < Cr < 3,5 % und 0,7% 1.7015, 1.7131, 1.7147, 1.7380, 1.7337, 1.7262, 1.7258, 1.7350, 1.7357, 1.7375, 1.7379, 1.7383, 1.7385, 1.7707, 1.8075 10CrMo9.10, 12CrMo9-10, 10CrSiMoV7, 12CrSiMo8, 30CrMoV9, GS-18CrMo9.10, 15CrMoV5-10, 16CrMo4-4, 15CrMo5, 24CrMo5, 22CrMo4-4, GS-17CrMo5-5, 15Cr3, 16MnCr5, 20MnCr5, 10CrSiV7, ASTM: A 387 Gr. 22, A217 Grade WC9, A335 Gr. P22, A217 Gr. WC9, A182 F22, A182 T22, A1031 Gr.5015, A1031 Gr.5115, A1031 Gr.4820							
GOEDKEURINGEN	CE							
LASPOSITIES	PAPBPCPDPEPFPG							
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	P	S	Cr	Mo	
	0.08	0.4	0.7	0.015	0.015	2.3	1.1	
MECHANISCHE WAARDEN	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V			Hardness
	675°C- 705°C 1h	580	750	20	RT	-20°C	0°C	HRc
HERDROGEN	Not required							
GAS ACC. EN ISO 14175	M21							



CEWELD AA M CrMo2

AA M CRM02 1,0MM

Packaging	KG/unit	EanCode
K-300	16	8720663423498

AA M CRM02 1,2MM

Packaging	KG/unit	EanCode
K-300	16	8720663423504