



CEWELD AA B350

TYPE	Seamless high basic flux core wire for Ar-CO2 mix					
TOEPASSINGEN	Pipe work, shipbuilding, steel and vessel construction, mechanical engineering.					
EIGENSCHAPPEN	Extremely crack resistant weld metal conditioned by the basic slag. Low spatter loss, easy slag removal. Well suited for joining high carbon steels and when welding critical mixed base metal combinations. Ideal metallurgical choice for repair welding and production as well as for use as a buffer layer. Developed for repair welding of pipes using half shells					
CLASSIFICATIE	AWS	A 5.20: E61T-G				
	EN ISO	17632-A: T 35 4 B M 1 H5				
	F-nr	6				
	FM	1				
GESCHIKT VOOR	Reh ≤ 350 MPa ISO 15608: 1.1, 1.2 1.0033, 1.0035, 1.0340, 1.0112, ...1.0426, 1.0473...1.0570 E155, S185, S235..S355, P235... P355 ASTM A284 Gr. C, D, A 830 M, A 516 M, A 299 M, A 573 M UNS G10220, SAE 1022 Armco Steels, Telar 75					
GOEDKEURINGEN	CE					
LASPOSITIES						
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C	Si	Mn	P	S	
	0.04	0.6	1.2	0.015	0.015	
MECHANISCHE WAARDEN	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V	
					-20°C	-40°C
	As Welded	350	500	27	100	80
						HRc
HERDROGEN	Not required					
GAS ACC. EN ISO 14175	M21					